

EXTRA

High performance tile adhesive.

Description

Extra is a polymer-modified cement-based tile adhesive, offering an improved bonding performance and resistance to frost and humidity; while it's increased thixotropic composition results in zero vertical slip. It is ideal for both indoors and outdoors tile installation on different substrates on walls and floor.

Usage and Application examples

Walls
Floors
Worktops(1)
Interior
Exterior (b)
Dry and wet environment

Substrates

Brick walls (2)
Concrete / Cement base mortars(2)
Plaster and Rendering (4)
Smooth prefabricated concrete
Cement and Plaster boards (2) (3) (4)
Fiber Cement (2)

- (1) Tiles must be grouted using EPOGROUT
(2) Provided that the surface is sufficiently flat and leveled
(3) Prime with diluted Superlat Latex 1:1 with water
(4) In wet conditions (eg bathrooms) apply first ELASTOSIL or AQUASIL FLEX
(5) Prime one layer of Supergrip 1:1 with water

Note: Certain types of natural stone (i.e. limestone, thin marble, travertine and some granite) may be susceptible to water staining. In this case, use of a BAUER rapid-setting white adhesive is recommended

*Further applications possible by adding Baulat to provide flexibility, increased adhesion and reduce water permeability.

Restrictions

Not suitable for timber, metal, painted surfaces, plastic or resilient materials, plywood walls or floors, tiling to existing glazed tiles or carpets.
Not suitable for screeds, plasters/renders, concrete not yet cured and affected by drying shrinkage.
Not suitable for organic-based waterproofing products or tiles submerged under water*.

Technical Specifications

Form: white or grey dry powder.

Dry mortar density: 1.4 kg/L.

Pot life: approximately 4 hours.

Time for minor adjustments: up to 20 minutes.

Open time: up to 20 minutes. Open time / minor adjustment time will be extended in colder temperatures, when fixing to impervious backgrounds or when fixing tiles of low porosity.

Slip: $\leq 0.5\text{mm}$

Consumption: 1,5-4,0 kg/m² May vary dependent on nature and flatness of surface, and on trowel used.

Application thickness: up to 12mm.

Application conditions: +5 °C to +35 °C

Service temperature: -15 °C to +60 °C

Adhesion to concrete, 28 days: $\geq 1\text{ N/mm}^2$.

Adhesion after heat ageing: $\geq 1\text{ N/mm}^2$.

Adhesion after freeze-thaw cycles: $\geq 1\text{ N/mm}^2$.

Adhesion after water immersion: $\geq 1\text{ N/mm}^2$.

Ready to use: after 7 days.

Grouting on walls: after 4-6 hours.

Grouting on floors: after 24 hours.

Substrate surface preparation

Substrates must be in sound condition, flat, solid, rigid, durable, dry without rising damp and free from any factors that prevent adhesion such as dust, grease, etc

Remove any loose material using suitable mechanical method.

Cement base screeds, must be allowed to cure completely and not be affected by drying shrinkage and have moisture contact $\leq 0,2\text{ CM-\%}$

Anhydrite screeds must have moisture contact $\leq 0,5\text{ CM-\%}$

Surface regularity: Surface regularity is defined as the deviation in height of the surface of a flooring layer over short distances in a local area. In simpler terms, it is the "flatness" or "measure of unevenness" of the screeded surface.

MAXIMUM PERMISSIBLE DEVIATION from a 2m straight edge in direct contact with the surface for Class SR1=3mm. Class SR1 surfaces are recommended for direct fixing of tiles and slabs with a tile adhesive.

For substrates with deviations in height > 3mm and up to 20mm it is advised to use one layer of Hardox Flu 300 self-leveling floor.

Ensure flat, clean, dry surfaces, free from any shrinking tendencies. Remove any loose material or detaches fragments, dust, grease etc. Seal off and repair any major gaps. For surfaces in direct contact with the ground (eg. Basements), make sure that uprising damp is eliminated.

SUITABLE SUBSTRATES

Allow the following minimum drying times:

- Concrete/concrete block/clay brickwork: more than 4 weeks.
- Cement: sand screed more than 3 weeks.
- Cement: sand renderings more than 2 weeks.
- Plaster more than 4 weeks.
- Special screed mortars (e.g. Self-levelling floors): according to the manufacturer instructions.

Note: For further information on other substrates/surfaces and preparation contact the Technical Department of BAUER

Mixture preparation

1. The adhesive must be prepared in a suitable container, by first pouring the required quantity of water and then gradually adding the contents of the bag, whilst stirring with an electric mixer at low speed (under 300 rpm).
2. The mixture should be mixed until a uniform lump-free homogeneous mortar is achieved.
3. The mixture must be left to rest for about 2-3 minutes and then stirred slightly again.

Water required for wall applications approximately 6,5 L for 1 bag of 25 Kg or 1,3 L for 1 bag of 5 Kg.
Water required for floor applications approximately 7,0 L for 1 bag of 25 Kg or 1,4 L for 1 bag of 5 Kg.

The quantity of water to be added, indicated on the packaging, is an approximate guide. It is possible to obtain mixtures with variable thixotropic consistency, according to the intended use. Adding much more water (>10%) than the prescribed ratio may result in reduction of the coating thickness during curing, and subsequently in a reduction of the strength of the mortar. Regular stirring (every 45-60 min) without adding water is recommended.

Note: The Pot life / setting time mentioned will vary slightly with the outside temperature. Higher temperature results in shorter; Lower temperature results in longer life and time.
Do NOT use in temperatures below 5°C or over 35°C.

Instructions for use

1. Apply the adhesive on the substrate using the appropriate notched metal trowel, according to needed bed thickness and comb to the required bed thickness, ensuring that the ribs of the adhesive all run in one direction and not in a circular pattern.
2. To ensure improved adhesion onto the substrate, first spread a thin coat of adhesive with the smooth side of the trowel and immediately apply the desired

adhesive thickness with the notched edge of the trowel, depending on the type and size of the tile to be installed. If the back of the tiles is dusty, we recommend washing with clean water. Within 10-15 min, fix tiles one by one and press them to ensure firm contact.

3. The adhesive may be applied in a bed thickness of 2 - 6 mm thick or even up to 12 mm in limited localized areas. If fixing large/heavy-patterned tiles, apply additional adhesive on the tiles back side (back buttering method).

4. For tiles installation: press the tile firmly into the ribs of the adhesive and into position with a slight twisting/sliding action to ensure the optimum adhesive contact with the back of the tile.

For mosaics installation: use a rubber tile float to press mosaics into the adhesive and beat into the required position.

To guarantee maximum adhesion it is necessary to apply a layer of adhesive sufficient to cover the entire back of the coating material.

Always check and clean the back of the tiles if dirty; we recommend washing with clean water.

5. Fix tiles/mosaics before the adhesive forms skin (typically more than 15 min at 20 °C, which greatly depends on the surface porosity and atmospheric conditions). In case skin has formed on the adhesive, remove the adhesive and apply a new fresh layer. Always discard any adhesive that has begun to set and never add further water.

It is always important before fixing the tiles, to ensure that the substrate is leveled (SR1) as per section "Surface Preparation" above. When using larger format tiles, it is essential that the substrate is as level as possible, ideally to better than SR1, as this will avoid excessive bedding out of adhesive and will reduce installation time.

In case of minor surface irregularities or if increased adhesive thickness is necessary for alignment, spread the surface with a layer of adhesive of the required thickness and another layer of adhesive in the back of the tile. Mount the tiles in place and press to ensure firm contact (at least 70%). For large tiles fixing outdoors and in areas with heavy traffic, apply the adhesive also on the back of the tile (back buttering method) to ensure 100% coverage.

Since open time under adverse weather conditions (sunlight, high temperatures, dry atmosphere etc) or on highly absorbent surfaces, can be reduced even to a few minutes, it is important to always check periodically with your fingers whether a membrane has formed on the surface of the adhesive. In such a case, remove the dried part and add a quantity of fresh adhesive. If the surface is left for a prolonged period and corrections are necessary, remove the tile, clean the adhesive from the surface and remount in the proper position.

6. Occasionally lift a tile/mosaic to check adhesive's surface contact on back of the tile/mosaic. When using the solid-bed method, make sure to leave no voids behind the tiles.

7. Leave adequate joints between individual tiles.

Create elastic expansion joints:

- $\approx 10 \text{ m}^2$ for outdoors applications
- $\approx 25 \text{ m}^2$ for indoors applications and
- every 8 m long, for long narrow applications.

Respect all structural, fractionizing and perimeter joints present in the substrate.

8. Clean off surplus adhesive from the tile face and between tile joints before the adhesive has dried, with water. After the adhesive has dried it will require mechanical methods to be removed.

General application guidelines

- Intended for Professional Use.
- Abide by any applicable Standard and National Regulations
- Do not use the adhesive to cover substrate anomalies greater than 15 mm.
- Environmental conditions, ventilation, substrate and application material absorbency are factors that may differentiate the adhesives' workability and curing time.
- Use a notched trowel suitable for the tile dimensions and required bed thickness.
- Guarantee a full-bed of adhesive without voids in all external applications.
- When applying tiles in gypsum & cement boards, always make sure that they are firmly fixed on the appropriate profile, prior to any tile installation. For underfloor heating applications, perform the required test heating cycles of the mortar prior to application according to standard EN 1264-4 clause 4.4.
- If necessary, ask for the safety data sheet.

Product Designation

It is classified as Improved Cementitious adhesive with reduced slip **C2TE** in accordance to European standard EN 12004.

Consumption

1.5-4 Kg/m²

Storage

Preferably in sheltered areas, protected from the sun and low in moisture, for at least 12 months from the production date.

Packages

Heavy duty paper bags, 25 kg each. Pallets of 1.200 kg.

Precautions and safety

The product contains cement and is classified as an irritant. No special precautions are necessary for product application except for standard precautions applicable to all construction operations i.e. using gloves and goggles; preventing prolonged skin contact, etc. In case of eye contact, immediately wash with plenty of water and seek medical advice if necessary. Collect empty bags and plastic covers and dispose of in refuse bins designated for this purpose. Consult instructions for safe use indicated on product packaging. For

more information please refer to the material safety data sheet of the specific product.

Notes

Technical data, properties, recommendations and information on BAUER products are supplied in good faith. They are based on the company's research and experience, provided that they are stored and applied under normal conditions. Given that in each case of application, the use of the materials and the conditions of the project as well as the overall environment, cannot be controlled by the company, the sole responsibility for the result lies with the end user of the product. No liability under any legal relationship can be established against the company, based on the information listed within this document. The present edition of this Technical Data Sheet automatically cancels any previous editions. The end user of the products should always refer to the latest Technical Data Sheet version, which is available at the product's official website.

Other information

BAUER BUILDING TECHNOLOGIES

Megara Industrial Estate, Attica

Tel: +30 210 5744222

Fax: +30210 5740777

Email: info@netbauer.com

[http:// www.netbauer.com](http://www.netbauer.com)

Frankfurt, Reg. No 312310 QM

Qualitätsmanagementsystem

Zertifiziert nach DIN EN ISO 9001



